

TopClay Tennisbelägging

Description	Needle punch tennis surface. Support layer of 100% structured polypropylene fibre with total impregnation, in-filled with crushed brick clay.
Destination	Outdoor and Indoor tennis courts.
Support layer	Hot rolled impermeable asphalt 0/4-0/6, non-porous concrete with cross-slope. Porous concrete. Porous asphalt. Base horizontal plane must be checked before starting installation. Deviations of 6 mm under a 3 meters rule will be tolerated. Outside this limit the base must be levelled using an appropriate and approved technical solution.
Colour	Red
Membrane Mass	1.400 g/m ² ± 10 %
Membrane Thickness	9 mm ± 10 %
Standard roll Width	2 m
Standard roll Length	36,20 m
Standard roll Weight	approx. 102 kg
Fire Rating	Bfl s1
Court markings	TOP CLAY® Line Paint and Finisher, approx. 65 kg per court.
Infill	0/1 mm TOP CLAY® approved clay infill 3 to 4,5 T. per court.
Adhesive	Two-component PU glue in stripes approx 750 g/m ²
Playing features	ITF Category 1 «Slow». Ball bounce and playing comfort identical to traditional clay courts.
Warranty	10 years Degressive Warranty (see warranty conditions, available upon request).
Maintenance	See TOP CLAY® Maintenance Guidelines.
Installation	See TOP CLAY® Installation Guidelines.
Certification	ISO 9001:2015. Certificate Number : IT 240282

